

## Approval & Reception Procedure

DMC – Departamento de Materiais de Construção	
<b>Waterproof Membrane</b>	Document No. <b>ARP/DMC/04</b>
	Date : <b>2010-07-01</b>
	Page No. <b>1 of 1</b>

### 1. Reference Standard

Project specification

### 2. Approval Procedure

The catalogue of waterproofing membrane materials shall be submitted.

For approval of the proposed materials, the project specification should be considered.

### 3. Reception Procedure

One thickness test shall be done per each 500 m<sup>2</sup> of coated area.

For each test, 10 test pieces of waterproofing membranes shall be collected from the coated area.

The 10 test pieces shall be taken from vertical surfaces, horizontal surfaces and the zones where water leakage is expected e.g. construction joints.

### 4. Acceptance Criteria

The average thickness of the 10 test pieces shall be greater than the specified thickness and no test piece is thinner than 80% of the specified thickness.

In case of non-compliance of the results, additional coating shall be applied and retest shall be done.